

BIOCLEAN ALPHA

Sterile Latex Gloves

AL300

About

BioClean Alpha™ Sterile Latex Gloves provide exceptional flexibility, and are anatomically shaped for enhanced wearer comfort. An extra thick beaded cuff adds strength and stability on the arm, and reduces the risk of the gloves tearing when donning.

Specifications

COMPATIBILITY:

ISO Class 4 & EU GMP Grade A

LENGTH:

300mm (12")

MATERIAL:

Latex

PROTEIN LEVEL:

Less than 50µg/gram

SURFACE:

Textured

SHAPE:

Hand specific

COLOUR:

Natural

STERILIZATION:

Gamma irradiation

Features


- Exceptional flexibility and comfort
- Extra thick beaded cuff to reduce tearing when donning
- Powder-free
- EasyOn™ proprietary technology allows for easy double-donning
- Non-particulating EasyTear™ packaging

EXTRA THICK CUFF

ANATOMICALLY SHAPED

EXCEPTIONAL FLEXIBILITY & COMFORT

DOUBLE-DONNABLE



Ms.G.Love© represents BioClean's range of cleanroom gloves

- Manufactured in a facility holding ISO 9001: 2008 and 89/686/EEC Article 11b certifications
- Conforms to Category 3 - Complex Design Personal Protective Equipment PPE Directive 89/686/EEC
- Processed in an NEBB certified ISO Class 4 environment
- Complies with the requirements of European Glove Standards EN420:2003 and EN374-1, 2 & 3:2003
- Physical properties comply with European Medical Glove Standard EN455-2:2009
- Sterilized in accordance with ISO 11137-1:2006
- Suitable for contact with dry, alcoholic and acidic foodstuffs.

Method: Gamma irradiation
Minimum Dose: 25kGy
Sterility Assurance Level: 10^{-6}

Five (5) years from date of manufacture.
Store in a dry, cool place ($<40^{\circ}\text{C}$) away
from direct sunlight and fluorescent
light.

CHARACTERISTICS	VALUE	TEST METHOD
Freedom From Holes	AQL 0.65 Performance Level 3	EN 374-2:2003
Glove Length +/-10mm (mm/inches)	290/11.4	EN 420:2003
Single Wall Thickness Minimum (mils/mm)	Cuff: 6.30/0.16 Palm: 7.09/0.18 Finger Tip: 7.87/0.20	EN 455-2:2009
Force At Break During Shelf Life	≥12 N	EN 455-2:2009

PALM WIDTHS (mm) \pm 5mm							
SIZE	6.0	6.5	7.0	7.5	8.0	8.5	9.0
mm	77	83	89	95	102	108	114
TEST METHOD				EN 420:2003			

PARTICLES					TYPICAL PARTICLE COUNT			TEST METHOD
≥ 0.5μm(counts/cm ²)					<3500			TEST-RP-CC005.4
TYPICAL EXTRACTABLE IONS								TEST METHOD
ANIONS	Fluoride	Chloride	Nitrite	Bromide	Nitrate	Phosphate	Sulphate	TEST-RP-CC005.4
(μg/cm ²)	0.002	2.480	NT	NT	0.900	NT	0.290	
CATIONS	Lithium	Sodium	Ammonium	Potassium	Calcium	Magnesium	Zinc	
(μg/cm ²)	NT	0.070	ND	0.135	1.525	0.001	NT	
ND = Not Detected, NT = Not Tested								

TO ORDER

Re-order code	Size	Packing
AL300-60	6.0	One pair per inner PE wallet; one wallet per sealed EasyTear™ PE pouch; 10 pouches per sealed outer PE bag; 20 outer bags per lined carton (200 pairs)
AL300-65	6.5	
AL300-70	7.0	
AL300-75	7.5	
AL300-80	8.0	
AL300-85	8.5	
AL300-90	9.0	

For additional information visit us at www.bioclean.com, or call us at +44 1638 663338

Nitritex Ltd

Minton Enterprise Park
Oaks Drive
Newmarket, Suffolk
CB8 7YY
United Kingdom

AL300/1806/PDS36

Ansell

Caution: This product contains natural rubber latex (latex) which may cause allergic reactions in some users. Safe use of this glove by or on latex sensitized individuals has not been established.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

*Warning: No glove provides complete protection against all chemicals. Users must test the gloves against the particular chemicals and environment in which they will be used.

**Please see product validation pack or contact Ansell customer service for specific data on use of gloves with cytotoxic drugs. Gloves used for protection against such drugs must be selected specifically for the type of chemicals used.

Ansell, ® and TM are trademarks owned by Ansell Limited or one of its affiliates. © 2012 – 2018 Ansell Limited. All Rights Reserved.