

#### **About**

BioClean Ultimate Sterile Polychloroprene Gloves offer good tactility for precision work and comfort for prolonged use. Offering resistance to a range of chemicals\* and antistatic properties the Ultimate is also latex-free and powderfree

# offer good tactility for precision ad comfort for prolonged use.

ANTISTATIC

CHEMICAL RESISTANCE\*

BIOCLEAN

ULTIMATE

Sterile Polychloroprene Gloves

DOUBLE-DONNABLE

## **Specifications**

COMPATIBILITY:

ISO Class 4 & EU GMP Grade A

LENGTH:

300mm (12")

MATERIAL:

Polychloroprene

PROTEIN LEVEL:

Polychloroprene contains no natural latex

proteins

SURFACE: Textured

SHAPE:

Hand specific

COLOUR:

Natural

STERILIZATION:

Gamma irradiation

## **Features**

- Powder-free & latex-free
- ESD properties
- · Beaded cuff for strength
- Chemical resistant\*
- Double-donnable
- Non-particulating EasyTear packaging





Ms.G.Love© represents BioClean's range of cleanroom gloves



# **Quality Standards**

- Manufactured in a facility holding ISO 9001: 2008 and 89/686/EEC
   Article 11b certifications
- Conforms to Category 3 Complex Design Personal Protective Equipment PPE Directive 89/686/EEC
- Processed in an NEBB certified ISO Class 4 environment
- Complies with the requirements of Glove Standard EN420:2003 and EN374-1, 2 & 3:2003
- Physical properties comply with European Medical Glove Standard EN455-2:2009
- Tested against permeation standard ASTM D6978-05 for cytotoxic drugs\*\*
- Sterilized in accordance with ISO 11137-1:2006
- Suitable for contact with all foodstuffs.

#### Physical Properties

CHARACTERISTICS	VALUE	TEST METHOD	
Freedom From Holes	AQL 0.65	EN 374-2:2003	
	Performance Level 3		
Glove Length	290/11.4	EN 420:2003	
+/-10mm (mm/inches)			
Single Wall Thickness	Cuff: 3.54/0.09	EN 455-2:2009	
Minimum (mils/mm)	Palm: 4.33/0.11		
	Finger Tip: 5.51/0.14		
Force At Break	≥ 3.6 N	EN 455-2:2009	
During Shelf Life			

#### Sterilization

Method: Gamma irradiation Minimum Dose: 25kGy Sterility Assurance Level: 10<sup>-6</sup>

#### Shelf Life & Storage

Five (5) years from date of manufacture. Store in a dry, cool place (<40°C) away from direct sunlight and fluorescent light.

PALM WIDTHS (mm) ± 5mm							
SIZE	6.0	6.5	7.0	7.5	8.0	8.5	9.0
mm	77	83	89	95	102	108	115
TEST METHOD			EN 420:2003				

#### Glove Cleanliness Characteristics

PARTICLES					TYPICAL PARTICLE COUNT			TEST METHOD
≥ 0.5µm(counts/cm²)					<1300			IEST-RP-CC005.4
TYPICAL EXTRACTABLE IONS					TEST METHOD			
ANIONS	Fluoride	Chloride	Nitrite	Bromide	Nitrate	Phosphate	Sulphate	IEST-RP-CC005.4
(μg/cm <sup>2</sup> )	ND	0.494	ND	ND	0.795	ND	0.041	
CATIONS	Lithium	Sodium	Ammonium	Potassium	Calcium	Magnesium	Zinc	
(μg/cm <sup>2</sup> )	ND	0.123	0.005	0.378	0.582	0.025	NT	
	NI	D = Not D	etected, NT =	Not Teste	d			







#### TO ORDER

Re-order code	Size	Packing
BUPS-60	6.0	One pair per inner PE wallet; one wallet per sealed EasyTear PE pouch; 10 pouches
BUPS-65	6.5	per sealed outer PE bag; 20 outer bags per lined carton (200 pairs)
BUPS-70	7.0	
BUPS-75	7.5	
BUPS-80	8.0	
BUPS-85	8.5	
BUPS-90	9.0	

For additional information visit us at www.bioclean.com, or call us at +44 1638 663338

Nitritex Ltd Minton Enterprise Park Oaks Drive Newmarket, Suffolk CB8 7YY United Kingdom

BUPS/1806/PDS37



Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

\*Warning: No glove provides complete protection against all chemicals. Users must test the gloves against the particular chemicals and environment in which they will be used.

\*\*Please see product validation pack or contact Ansell customer service for specific data on use of gloves with cytotoxic drugs. Gloves used for protection against such drugs must be selected specifically for the type of chemicals used.

Ansell, ® and TM are trademarks owned by Ansell Limited or one of its affiliates. © 2012 – 2018 Ansell Limited. All Rights Reserved.